



TECHNICAL DATA SHEET

KRAFTLINER

Mark: K1

End-uses

KRAFTLINER uses for flat layers of corrugated cardboard.

Grammages

KRAFTLINER is available in a basis weight range between 115 and 150 g/m²

Certification

Production of KRAFTLINER is certified according to the quality system ISO 9001-2011.
Voluntary forest certification FCS.

Properties	Unit	Standard	Typical Values			
			115	125	140	150
Basis Weight	g/m ²	GOST 13199 ISO 536	115	125	140	150
			110-120	118-132	132-148	141-159
Thickness	mm	GOST 27015 ISO 439, 534	0,16-0,21	0,18-0,24	0,21-0,27	0,23-0,29
Absolute bursting resistance, not less	kPa (kgs/cm ²)	GOST 13525,8 ISO 2758, 2759	400(4,0)	460(4,7)	490(5,0)	520(5,3)
Breaking force at ring compressing in the transverse direction, not less	H (kgs)		-	150(15)		
Surface water absorption at unilateral wetting (Cobb60) of the upper side, no more	g/m ²	GOST 12605 ISO 535	30			
Moisture, no more	%	GOST 13525,19 ISO 287	6-9			

Paper color conforms the color of natural fibre.

The Products meets the requirements of the technical specifications

Country of goods origin - Russian Federation